

VELOSIT® SL 502

Universal Self Leveling Underlayment and Polishable Overlay



Application fields

VELOSIT SL 502 is a cementitious self leveling underlayment and overlayment for concrete substrates. It creates a very smooth surface for coatings and floor coverings. Typical application fields besides others are as follows:

- Interior and exterior use
- Suitable for permanent immersion in water
- Leveling of concrete slabs and floors
- Cosmetic repair of surface defects on concrete floors
- Structural repair of concrete
- Application thickness from 1/8" (3 mm) to 1 1/2" (38 mm). 5" (13 cm) when extended with aggregate
- Polishable -Polished Final Wear Surface
- Self leveling screed
- Floor heating systems

Properties

VELOSIT SL 502 is a shrinkage compensated cementitious self leveling underlayment with very quick strength development. VELOSIT SL 502 binds the mixing water very quickly allowing a very short wait time before it can be covered. VELOSIT SL 502 creates a well bonded and very smooth layer on the substrate.

VELOSIT SL 502 can be applied by rake or suitable pumping equipment.

- Minimal shrinkage/expansion under dry or wet curing conditions minimizing the risk of micro-cracking
- Excellent flow with long pot life
- Smooth surface profile
- Fast air release with minimal requirement for agitation
- Ready for covering with ceramic tiles after 4 hours, for moisture sensitive floor coverings after 12 hours.
- 30 - 40 min. working time and 2340 psi (16 MPa) compressive strength after 4 hours
- Final strength of more than 7250 psi (50 MPa) after 28 days

velosit

- Open to foot traffic after 3 hours
- Excellent adhesion to properly prepared concrete
- Good resistance against CO₂ and Chloride penetration due to a very tight pore structure
- Excellent water resistance, no strength loss under water
- Good weathering resistance
- Good sulfate resistance
- Light gray color close to concrete color

Application

1.) Substrate preparation

VELOSIT SL 502 is designed for concrete substrates. Steel may be coated with a suitable bonding bridge. Also plywood or OSB-floors with an engineers design for minimal deflection can be coated.

a.) Steel must be prepared to white metal.

b.) Concrete substrates must be prepared with sand blasting, shot blasting or high pressure water blasting (>3000 psi) to remove all bond breaking substances.

Substrate must be rough, open porous and load bearing. The minimum requirement for adhesive strength is 218 psi (1.5 MPa) and for the compressive strength 3450 psi (25 MPa). Lower strength values can be accepted if lower adhesive strength is acceptable. Active water leaks must be treated and fully stopped with VELOSIT PC 221/222. Leaking cracks need to be sealed with a suitable VELOSIT IR injection resin.

c.) Wooden substrates must be free from bond breaking substances. Otherwise the surface must be sanded before priming.

Priming:

a.) Steel: Apply a corrosion protection coat on rebar with VELOSIT CP 201. Other steel areas can be primed with VELOSIT PR 303 with a full broadcast. Steel may expand and contract differently under temperature changes than a

cementitious mortar. Thus steel application is only recommended if steel is embedded in larger concrete bodies or the temperature is not subject to major changes.

b.) Concrete substrates with a humidity of max. 4% and a water vapor emission rate of less than 3 lbs/24h x 1000 ft² or 75% R.H. can be primed with VELOSIT PA 911 (Acrylic Primer).

VELOSIT PA 911 is ready to receive the leveler usually after 2-3 h curing. At higher moisture levels or in case the moisture levels in the substrate are expected to increase, priming must be done with VELOSIT PR 303 moisture mitigating primer. VELOSIT SL 502 can be applied into the tacky PR 303 primer within 2-4 hours after application. Longer wait times (over 5 days) require a full broadcast with a 50-70 mesh clean dry silica sand into the primer.

c.) Wooden substrates must be primed with VELOSIT PA 911. Wood substrates swell with water. An overlay is only permitted if these are completely dry before the application and no negative side water source will impact the topping later on. Wood is generally not a sufficiently load bearing substrate to achieve high adhesive strengths. A mechanically fastened mesh can increase the bond to the wood substrate.

2.) Processing

Mixing: Mix VELOSIT SL 502 with 19-20% potable water, i.e. 1.2 – 1.3 gal (4.8-5.0 l) water per 55 lb (25 kg) bag. Fill the 19% mixing water (1.2 gal per bag) into a suitable bucket and mix the powder with a slow speed drill (300-600 rpm) into the water until a lump-free mix is achieved. Use a cage type mixing paddle to reduce the air entrainment into the mix. Add max. 1% additional water under stirring until the desired consistency is achieved. Do not over water the product!

The product is workable for 30-40 min. at 70°F.

a.) Rake application: Pour VELOSIT SL 502 onto the primed substrate and rake to the desired thickness. Make sure there are no bond breaking substances on the primer. The product can be applied up to 1 ½ " (38 mm) in one application. Make sure to work in sections that

can be finished within 30 min. Immediately after pouring use gauge rake to achieve thickness and force entrapped air to the surface. Alternatively a spiked roller can be used to help air to surface at larger application thickness. Finish with a smooth rake.

b.) Pump application: In mixing pumps feed the powder into the product hopper and adjust the water to the specified rate. The water rate can be adjusted by comparing the flow with a hand-mixed batch with a correct water addition. Control the flow with a flow cone every 5 to 10 min. With mortar pumps add the mixed product as described above into the feed hopper of the pump and pump continuously. Rake and smooth the material as described under section a.). Long pump interruptions may result in clogging of the pump hose. The product may cure a lot faster if the hose is exposed to direct sunlight. Always empty and flush the machine after pumping or before long spray interruptions. VELOSIT SL 502 is a fast curing material and may be hard to remove if left in the machine.

Never overcoat joints or untreated cracks as this will most likely result in surface cracks!

3.) Curing

VELOSIT SL 502 does not require curing. Protect the applied product for 24 hours against direct sun light, wind and temperature changes exceeding 9°F(5°C).

Estimating

Volume yield:
55 lbs (25 kg) VELOSIT SL 502 result in approx. 0.49 ft³ (14 l) cured leveler. 27 sqft/bag at 1/4" (6mm).

Cleaning

VELOSIT SL 502 can be removed in the fresh state with water. Once it has cured acidic cleaners like muriatic acid and mechanical cleaning are required.

Quality features

Color:	gray
Mixing ratio by weight:	100 : 19
Mixing ratio by volume:	100 : 30
Density:	1.6 kg/l
Substrate temperature:	50 – 95°F (10-35°C)
Initial set:	55 min.
Final set:	105 min.
Compressive / flexural strength:	
4 hours:	2340/435 psi (16/3 MPa)
24 hours:	4350/725 psi (30/5 MPa)
7 days:	5945/1015 psi (41/7 MPa)
28 days:	7540/1160 psi (52/8 MPa)
Chloride ions:	< 0.05%
Carbonation resistance:	passed
Capillary water absorption:	0.1 kg/m ² x h ^{0.5}
Adhesive strength**:	
- primed with PR 303:	261 psi (1.8 MPa)
- primed with PA 911:	218 psi (1.5 MPa)
Restrained shrinkage:	247 psi (1.7 MPa)
Length change after 56 days	
- dry storage:	-0.5 mm/m (-0.05%)
- water storage:	+0.0 mm/m (+0.00%)
Fire rating EN13501-1:	Class A1

Packaging

VELOSIT SL 502 is available in 55 lb (25 kg) watertight plastic bags.

Storage

VELOSIT SL 502 can be stored in unopened original packs for 12 months at 40-95°F (5-35°C) in a dry storage place protected against sunlight.

Safety

Please observe the actual valid material safety data sheet and follow the described safety measures for handling of the product.

Recommendations

VELOSIT SL 502 is only available for professional applicators.

Never add water to VELOSIT SL 502 when it has started to set. Stiffened material must be disposed.

All described product features are determined under controlled laboratory conditions according to the relevant international standards. Values determined under job site conditions may deviate from the stated values. Velosit USA LLC warrants this product for a period of 1 year from the date of installation to be manufactured without defects and to be consistent with printed technical characteristics. Velosit USA LLC makes no warranty as to merchantability or fitness for a particular purpose and this warranty is in lieu of all other warranties expressed or implied.

Please always use the latest version of this data sheet available from our website
www.velosit-usa.com

Effective date

July 2014

Manufacturer

VELOSIT GmbH & Co. KG
Industriepark 7
32805 Horn-Bad Meinberg
Germany