

VELOSIT® SC 244

Rapid SCC Patching/Overlay

Application fields

VELOSIT SC 244 is a ready-to-use cementitious Self Consolidating Concrete mix. It is mixed on site creating a rapid hardening overlayment. It is ready to receive traffic in 4 hours and flooring systems within 24 hours.

Typical application fields besides others are as follows:

- Interior and exterior use
- Bonded screeds
- De-coupled screeds on insulation or membranes
- Job site concrete mix-Overlay

Properties

VELOSIT SC 244 is a shrinkage compensated ready for use screed formulation with very quick strength development. VELOSIT SC 244 binds the mixing water very fast allowing a very short wait time before it can be covered.

VELOSIT SC 244 can be applied by rake or suitable pumping equipment.

- Minimal shrinkage/expansion under dry or wet curing conditions minimizing the risk of micro-cracking
- Excellent workability
- Fiber reinforced
- Ready for covering with ceramic tiles after 4 hours, for moisture sensitive floor coverings after 24 hours.
- 40 min. working time and 1840 psi (12 MPa) compressive strength after 4 hours
- Final strength of more than 7250 psi (50 MPa) after 28 days
- Open to foot traffic in 2-4 hours
- Very good adhesion to properly prepared concrete
- Excellent water resistance, no strength loss under water
- High tensile strength allowing thin applications on de-coupled screed applications
- Good weathering resistance
- Good sulfate resistance
- Light gray color close to concrete color

Application

1.) Substrate preparation

Bonded screed application

VELOSIT SC 244 is designed for concrete substrates. Steel may be coated with a suitable bonding bridge like VELOSIT CP 201

a.) Steel must be prepared to white metal

b.) Concrete substrates must be prepared with sand blasting, shot blasting or high pressure water blasting (min. 3000 psi) to remove all bond breaking substances.

Substrate must be rough, open porous and load bearing. The minimum requirement for adhesive strength is 145 psi (1 MPa) and for the compressive strength 2900 psi (20 MPa). Lower strength values can be accepted if lower adhesive strength is acceptable. Active water leaks must be treated and fully stopped with VELOSIT PC 221. Leaking cracks need to be sealed with a VELOSIT injection material.

Priming:

a.) Steel: Apply a corrosion protection coat on rebar with VELOSIT CP 201. Other steel areas can be primed with VELOSIT PR 303 with a full broadcast. Steel may expand and contract differently under temperature changes than a cementitious mortar. Thus steel application is only recommended if steel is embedded in larger concrete bodies or the temperature is not subject to major changes.

b.) Concrete substrates must be primed with VELOSIT CP 201 and the screed can be applied wet in wet immediately after priming.

De-coupled screeds

a.) Insulation boards (EPS, XPS etc.) must be laid out on a solid substructure that prevents future settlement. A PE membrane is mandatory to avoid the screed mortar entering the joints and building bridges to the substrate. Use de-coupling strips on the wall termination. Seal membrane overlaps with tape.

b.) Existing membranes like bitumen sheets can be covered directly with a VELOSIT SC 244 based screed.

c.) Wooden substrates must be covered with a de-coupling membrane (for example PE sheet).

2.) Processing

Mixing: VELOSIT SC 244 requires 10-10.5% potable water, i.e. 0.7 gal (2.5 l) water per 55 lb (25 kg) bag. Fill 10% mixing water (10 l per 4 bags) into a mixer and add 4 bags of VELOSIT SC 244 and mix for 2 min. Check the consistency and add water to adjust the desired consistency (total water not to exceed 10.5 l). Small volumes can be hand-mixed in a suitable bucket. Add the calculated water amount and add the powder mix afterwards with a slow speed drill (300-600 rpm) into the water until a lump-free mix is achieved. Do not over water the product!

The product is workable for 40 min. at 70°F.

a.) Rake application: Pour VELOSIT SC 244 screed onto the prepared substrate and level with a rake to the desired thickness and agitate to remove air. Make sure to work in sections that can be finished within 30 min.

b.) Pump application: Suitable mortar pumps are for example:

- Brinkmann GmbH: Estrichboy FHS 200/3
- PFT GmbH: G4

Feed VELOSIT SC 244 into the product hopper and adjust the water to the specified rate. The water rate can be adjusted by comparing the flow with a hand-mixed batch with a correct water addition. Control the flow with a flow cone every 10 min. Pump continuously and spread the material with a rake to the desired thickness. Agitate to remove entrained air. Make sure to work in sections that can be finished within 30 min. Long pump interruptions may result in clogging of the pump hose. The product may cure a lot faster if the hose is exposed to direct sunlight. Always empty and flush the machine after pumping or before long pump interruptions. VELOSIT SC 244 is a fast curing material and may be hard to remove if left in the machine.

Never overcoat joints or untreated cracks as this will most likely result in surface cracks!

3.) Curing

VELOSIT SC 244 is a cement based screed and does not require curing. Protect the applied product for 24 hours against direct sun light, wind and temperature changes exceeding 9°F (5°C).

Estimating

Volume yield:
55 lbs (25 kg) VELOSIT SC 244 result in approx. 0.46 ft³ cured patch or overlay. Up to 33 lbs of 3/8" pea gravel can be added to 1 bag of VELOSIT SC 244

Consumption per 10 ft²:
1/2" thickness: 45 lb (20.5 kg)
1.5" thickness: 180 lb (82.0 kg)
2" thickness: 225 lb (102.5 kg)

Cleaning

VELOSIT SC 244 screeds can be removed in the fresh state with water. Once it has cured acidic cleaners like muriatic acid and mechanical cleaning are required.

Quality features

Color:	gray
Water demand:	10 - 10.5 %
Density:	1.68 kg/l
Substrate temperature:	50 – 85°F* (10-35°C)
Initial set:	90 min.
Final set:	120 min.
Compressive / flexural strength:	
4 hours:	1985/290 psi (13/2 MPa)
24 hours:	3770/580 psi (26/4 MPa)
7 days:	6090/870 psi (42/6 MPa)
28 days:	7395/1015 psi (51/7 MPa)
Adhesive strength**:	
- primed with CP 201:	309 psi (2.2 MPa)
Length change after 56 days	
- dry storage:	-0.4 mm/m (-0.02%)
- water storage:	+0.0 mm/m (+0.00%)

Fire rating EN13501-1: Class A1
**acc. EN 1542. Adhesion depends very much on proper surface preparation!

Packaging

VELOSIT SC 244 is available in 55 lb (25 kg) watertight plastic bags or 3,300 lb (1500 kg) Supersacks.

Storage

VELOSIT SC 244 can be stored in unopened original packs for 12 months at 40-95°F (5-35°C) in a dry storage place protected against sunlight.

Safety

Please observe the actual valid material safety data sheet and follow the described safety measures for handling of the product.

Recommendations

VELOSIT SC 244 is only available for professional applicators.

Never add water to VELOSIT SC 244 when it has started to set. Stiffened material must be disposed.

All described product features are determined under controlled laboratory conditions according to the relevant international standards. Values determined under job site conditions may deviate from the stated values. Velosit USA LLC warrants this product for a period of 1 year from the date of installation to be manufactured without defects and to be consistent with printed technical characteristics. Velosit USA LLC makes no warranty as to merchantability or fitness for a particular purpose and this warranty is in lieu of all other warranties expressed or implied.

Please always use the latest version of this data sheet available from our website
www.velosit-usa.com

Effective date

December 2015

Manufacturer

VELOSIT GmbH & Co. KG
Industriepark 7
32805 Horn-Bad Meinberg
Germany